

Matte side heat sealable, other side treated, matte BOPP film.

Properties

- One side matte finish surface
- Lower light reflection for easy viewing
- Luxurious feel giving quality image

Applications

Designed for different look snacks packaging, book cover and other stationary products.

PROPERTIES	TEST CONDITIONS		UNITS	TYPICAL VALUES			
THICKNESS		μ	15	18	20	25
			Gauge	60	72	80	100
THICKNESS TOLERANCE		%	5			
UNIT WEIGHT	ASTM D 2673		g / m ²	13.7	16.3	18.1	22.6
YIELD	ASTM D 2673		m ² / kg	72.9	61.3	55.2	44.2
HAZE	ASTM D 1003		%	75 ± 5			
GLOSS	ASTM D 2457		%	Glossy side 55 ± 5 Matte side 10 ± 1			
OPTICAL DENSITY	MACBETH				
COEFFICIENT OF FRICTION*	ASTM D 1894	B/B*	< 0.35			
		B/M*		< 0.25			
TENSILE STRENGTH	ASTM D 882	MD	N/mm ²	120 ± 20			
		TD		270 ± 50			
ELONGATION AT BREAK	ASTM D 882	MD	%	170 ± 30			
		TD		45 ± 10			
HEAT SEAL TEMPERATURE	3 Bar / 0.5 Sec		°C	110 - 145			
SEAL STRENGTH	130°C / 3 Bar / 0.5 Sec		N / 15mm	> 2.3			
WVTR	ASTM F 1249 38°C / 90% RH		g / m ² / day	< 6.0			
TREATMENT LEVEL	ASTM D 2578		dyne / cm	≥ 38			
HEAT SHRINKAGE	130°C / 7 min	MD	%	≤ 5.0			
		TD		≤ 3.0			

*B/B : Nontreated side to nontreated side

*All COF values are dynamic results

*B/M : Nontreated side to metal

The above information is the result of laboratory test which are applied on samples from standart production. Since the varying conditions under which our products used are beyond our control, all of the above results are without guarantee and warranty.

POLİBAK Plastik Film San. ve Tic.A.Ş. AOSB İzmir-TURKIYE

Phone : +90 232 3767970 Fax : +90 232 3767730

E-Mail : polibak@polibak.com.tr www.polibak.com.tr

Reference No : 2017/02/00