

Both sides heat sealable, one side treated, white opaque (cavitated) BOPP film.

Properties

- Good stiffness
- High gloss printing side
- Economical printing capability due to white opaque colour

Applications

Designed especially for ice-cream packaging, lamination purposes and cold seal applications.

PROPERTIES	TEST CONDITIONS	UNITS	TYPICAL VALUES			
THICKNESS	μ	30	35	38	40
		Gauge	120	140	152	160
THICKNESS TOLERANCE	%	5			
UNIT WEIGHT	ASTM D 2673	g / m ²	21 ± 1.0	24.5 ± 1.0	26.6 ± 1.0	28 ± 1.0
YIELD	ASTM D 2673	m ² / kg	47.6 ± 2.0	40.8 ± 2.0	37.6 ± 2.0	35.7 ± 2.0
HAZE	ASTM D 1003	%			
GLOSS	ASTM D 2457	%	90 ± 10			
OPTICAL DENSITY	MACBETH	0.55 ± 0.05			
COEFFICIENT OF FRICTION*	ASTM D 1894	B/B*			
		B/M*				
TENSILE STRENGTH	ASTM D 882	MD	90 ± 20			
		TD	200 ± 50			
ELONGATION AT BREAK	ASTM D 882	MD	140 ± 20			
		TD	38 ± 5			
HEAT SEAL TEMPERATURE	3 Bar / 0.5 Sec	°C	110 - 145			
SEAL STRENGTH	130°C / 3 Bar / 0.5 Sec	N / 15 mm	> 2.0			
WVTR	ASTM F 1249 38°C / 90% RH	g / m ² / day	6.0			
TREATMENT LEVEL	ASTM D 2578	dyne / cm	≥ 38			
HEAT SHRINKAGE	130°C / 7 min	MD	≤ 5.0			
		TD	≤ 3.0			

*B : Back side

*All COF values are dynamic results

*M : Metal

The above information is the result of laboratory test which are applied on samples from standart production. Since the varying conditions under which our products used are beyond our control, all of the above results are without guarantee and warranty.

POLİBAK Plastik Film San. ve Tic.A.Ş. AOSB İzmir-TURKIYE

Phone : +90 232 3767970 Fax : +90 232 3767730

E-Mail : polibak@polibak.com.tr www.polibak.com.tr

Reference No : 2021/03/01