DULL2



Reference No: 2016/03/00

Non heat sealable, both sides treated, matt BOPP film.

Properties

- One side matt finish surface
- · Lower light reflection for easy viewing
- Luxurious feel giving quality image

Applications

Designed for different look snacks packaging, book cover and other stationary products.

| PROPERTIES | TEST CONDITIONS | | UNITS | TYPICAL VALUES | |
|--------------------------------------|------------------------------|------|--------------|---------------------------------------|------|
| THICKNESS | | | μ | 13 | 15 |
| THICKINESS | | | Gauge | 52 | 60 |
| THICKNESS TOLERANCE | | | % | 5 | |
| UNIT WEIGHT | ASTM D 2673 | | g / m² | 11.8 | 13.6 |
| YIELD | ASTM D 2673 | | m² / kg | 84.7 | 73.5 |
| HAZE | ASTM D 1003 | | % | 75 ± 5 | |
| GLOSS | ASTM D 2457 | | % | Glossy side 55 ± 5 Matte side 9.0 ± 1 | |
| OPTICAL DENSITY | MACBETH | | | | |
| COEFFICIENT OF FRICTION ² | ASTM D 1894 | B/B* | | < 0.45 | |
| | | B/M* | | < 0.30 | |
| TENSILE STRENGTH | ASTM D 882 | MD | - N/mm² | 120 ± 20 | |
| | | TD | | 270 ± 50 | |
| ELONGATION AT BREAK | ASTM D 882 | MD | - % | 170 ± 30 | |
| | | TD | | 45 ± 10 | |
| HEAT SEAL TEMPERATURE | 3 Bar / 0.5 Sec | | °C | | |
| SEAL STRENGTH | 130°C / 3 Bar / 0.5 Sec | | N / 15mm | | |
| WVTR | ASTM F 1249 38°C / 90% RH | | g / m² / day | 8.0 | |
| TREATMENT LEVEL | ASTM D 2578 | | dyne / cm | ≥ 38 (both) | |
| HEAT SHRINKAGE | 130°C / 7 mln | MD | - % | ≤ 5.0 | |
| | | TD | | ≤ 3.0 | |

*B : Back side

*All COF values are dynamic results

*M : Metal

The above information is the result of laboratory test which are applied on samples from standart production. Since the varying conditions under which our products used are beyond our control, all of the above results are without guarantee and warranty.

POLİBAK Plastik Film San. ve Tic.A.Ş. AOSB Izmir-TURKIYE Phone: +90 232 3767970 Fax: +90 232 3767730 E-Mail: polibak@polibak.com.tr www.polibak.com.tr