## **MEC-N**



Reference No: 2018/07/00

One side wide seal range heat sealable, other side treated, metallized BOPP film. MEC-N is the eco-friendly version of MEC.

## **Properties**

- Biodegradable in landfill after disposal
- · Eco-friendly film

## **Applications**

Biodegradable film widely used in single web and laminate structures for food packaging applications. It can be integrated within the standard recycle stream.

| PROPERTIES               | TEST CONDITIONS              |      | UNITS                   | TYPICAL VALUES |
|--------------------------|------------------------------|------|-------------------------|----------------|
| THICKNESS                |                              |      | μ                       | 30             |
| THICKNESS                |                              |      | Gauge                   | 120            |
| THICKNESS TOLERANCE      |                              |      | %                       | 5              |
| UNIT WEIGHT              | ASTM D 2673                  |      | g / m²                  | 27.2           |
| YIELD                    | ASTM D 2673                  |      | m² / kg                 | 36.7           |
| HAZE                     | ASTM D 1003                  |      | %                       |                |
| GLOSS                    | ASTM D 2457                  |      | %                       |                |
| OPTICAL DENSITY          | MACBETH                      |      |                         | 2.4            |
| COEFFICIENT OF FRICTION* | ASTM D 1894                  | B/B* |                         | < 0.40         |
|                          |                              | B/M* |                         | < 0.25         |
| TENSILE STRENGTH         | ASTM D 882                   | MD   | - N/mm²                 | 120 ± 20       |
|                          |                              | TD   |                         | 270 ± 50       |
| ELONGATION AT BREAK      | ASTM D 882                   | MD   | - %                     | 190 ± 40       |
|                          |                              | TD   |                         | 45 ± 10        |
| HEAT SEAL TEMPERATURE    | 3 Bar / 0.5 Sec              |      | °C                      | 110 - 145      |
| SEAL STRENGTH            | 130°C / 3 Bar / 0.5 Sec      |      | N / 15mm                | > 3.0          |
| WVTR                     | ASTM F 1249<br>38°C / 90% RH |      | g / m² / day            | ≤ 0.3          |
| OTR                      | ASTM D 3985<br>23°C / 0% RH  |      | cm <sup>3</sup> /m²/day | ≤ 80           |
| HEAT SHRINKAGE           | 130°C / 7 mln                | MD   | %                       | ≤ 5.0          |
|                          |                              | TD   |                         | ≤ 3.0          |

\*B: Back side

\*All COF values are dynamic results

\*M : Metal

The climatic and storage conditions may influence the metallised surface treatment.

In-line corona treatment is recommended for lamination. An adequate primer on the metallized surface is suggested for printing.

The above information is the result of laboratory test which are applied on samples from standart production. Since the varying conditions under which our products used are beyond our control, all of the above results are without guarantee and warranty.

POLİBAK Plastik Film San. ve Tic.A.Ş. AOSB Izmir-TURKIYE Phone: +90 232 3767970 Fax: +90 232 3767730 E-Mail: polibak@polibak.com.tr www.polibak.com.tr